

HiFill® POM HO IM3 HF

Acetal (POM) Homopolymer
Techmer Engineered Solutions

Message:

HiFill® POM HO IM3 HF is an Acetal (POM) Homopolymer product. It can be processed by injection molding and is available in North America. Characteristics include:
Homopolymer
Impact Modified

General Information			
Additive	Impact Modifier		
Features	Homopolymer		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.5	%	ASTM D955
Water Absorption (24 hr)	0.40	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	116		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	51.7	MPa	ASTM D638
Tensile Elongation (Break)	80	%	ASTM D638
Flexural Modulus	2210	MPa	ASTM D790
Flexural Strength	67.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	120	J/m	ASTM D256
Unnotched Izod Impact	640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	154	°C	
1.8 MPa, Unannealed	76.7	°C	
CLTE - Flow	1.1E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	ASTM D257

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

