

TPX® RT31XB

Polymethylpentene Copolymer

Mitsui Chemicals, Inc.

Message:

TPX®RT31XB is a polymethylpentene copolymer (PMP copolymer) material. This product is available in North America and is processed by film extrusion, fiber (spinning) extrusion or injection molding.

TPX®The main features of RT31XB are:

Hard

odorless/tasteless channel

TPX®The typical application areas of RT31XB are: food contact applications

General Information			
Features	Rigidity, high		
	The smell is low to none		
Agency Ratings	FDA not rated		
	JHOSPA not rated		
	European 2002/72/EC		
Appearance	Transparent-Light Blue		
Forms	Particle		
Processing Method	Film extrusion		
	Fiber (spinning) extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.833	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	21	g/10 min	ASTM D1238
Spiral Flow ¹	51.0	cm	Internal method
Molding Shrinkage ²			Internal method
Flow	1.5	%	Internal method
Transverse flow	1.2	%	Internal method
Water Absorption (24 hr)	< 0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	87		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1900	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield, 23°C	30.0	MPa	ASTM D638
Fracture, 23°C	25.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	12	%	ASTM D638
Flexural Modulus (23°C)	1600	MPa	ASTM D790

Flexural Strength (23°C)	44.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	20	J/m	ASTM D256
Unnotched Izod Impact Strength (23°C)	9.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	127	°C	ASTM D648
Vicat Softening Temperature	174	°C	ASTM D1525
Melting Temperature	233	°C	DSC
CLTE - Flow	1.2E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	65	kV/mm	ASTM D149
Dielectric Constant	2.10		ASTM D150
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.460		ASTM D542
Transmittance	94.0	%	ASTM D1003
Haze	0.80	%	ASTM D1003
NOTE			
1.	Mold temperature: 73°C, melt temperature: 310 to 320°C		
2.	temperature range: 260 to 280°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

