

VITAMIDE® BR16BK9504

Polyamide 6
Jackdaw Polymers

Message:

VITAMIDE® BR16BK9504 is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber. It is available in Europe. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792, ISO 1183
Water Absorption (23°C, 24 hr)	1.4	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	120	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	2.0	%	ASTM D638, ISO 527-2
Flexural Modulus	7000	MPa	ASTM D790, ISO 178
Flexural Stress			
--	165	MPa	ISO 178
Break	165	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	8.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	40	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	215	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	205	°C	ASTM D648, ISO 75-2/A
Peak Melting Temperature	220	°C	ASTM D2117, ISO 1218
CLTE - Flow	3.2E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257, IEC 60093
Dielectric Strength	60	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (Solution A)	550	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Glow Wire Ignition Temperature ¹	650	°C	IEC 60695-2-13
Oxygen Index	22	%	ASTM D2863, ISO 4589-2
NOTE			
1.	30 sec		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

