

Spartech Polycom SC5-2015

Polypropylene Copolymer

Spartech Polycom

Message:

Spartech SC5-2015 is a low viscosity PP copolymer resin for injection molding that features excellent process stability, good impact strength, and high stiffness. This product complies with FDA regulations and thus may be safely used in food contact and packaging applications. Polypropylene is a versatile thermoplastic offering a useful balance of heat and chemical resistance, good mechanical and electrical properties and processing ease. PP is resistant to deformation at elevated temperatures and resistant to impact at low temperatures. A very versatile product for a wide variety of applications, Spartech SC5-2015 is recommended for packaging, houseware and consumer product applications.

General Information			
Features	Low viscosity		
	Rigid, good		
	Copolymer		
	Impact resistance, good		
	Workability, good		
	Good electrical performance		
	Low temperature impact resistance		
	Good chemical resistance		
	Heat resistance, high		
	Compliance of Food Exposure		
Uses	Packaging		
	Household goods		
Agency Ratings	FDA Food Exposure, Not Rated		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	25.9	MPa	ASTM D638
Flexural Modulus (23°C)	1050	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	85	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	90.6	°C	

Drying Time	1.0	hr
Rear Temperature	216 - 227	°C
Middle Temperature	221 - 232	°C
Front Temperature	227 - 238	°C
Nozzle Temperature	232 - 243	°C
Processing (Melt) Temp	204 - 260	°C
Mold Temperature	26.7 - 37.8	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

