

ResMart Ultra PC HF UV

Polycarbonate

ResMart

Message:

High performance high flow polycarbonate with UV

General Information			
Additive	UV stabilizer		
Features	High liquidity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	22	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	62.1	MPa	ASTM D638
Flexural Modulus	2310	MPa	ASTM D790
Flexural Strength	91.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	590	J/m	ASTM D256
Unnotched Izod Impact	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	125	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	V-2		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance	90.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	116 - 121	°C	
Drying Time - Desiccant Dryer	4.0	hr	
Suggested Max Moisture	0.20	%	
Processing (Melt) Temp	288 - 316	°C	
Mold Temperature	82.2 - 121	°C	
Injection Pressure	68.9 - 103	MPa	
Injection instructions			

Dew Point: -20°F

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

