

Celstran® +PP-GF20-05CN05 Black

Polypropylene Copolymer

Celanese Corporation

Message:

Material code according to ISO 1043-1: PP

Polypropylene with 20 weight percent ash content, long glass fibers reinforced. Impact modified, copolymer. The fibers are chemically coupled to the polypropylene matrix. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long.

Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly.

The very isotropic shrinkage in the molded parts minimizes the warpage.

Complex parts can be manufactured with high reproducibility by injection molding.

Application field: Functional/structural parts for automotive

General Information			
Filler / Reinforcement	Long glass fiber, 20% filler by weight		
Additive	Impact modifier		
Features	Impact modification		
	Low warpage		
	Rigidity, high		
	High strength		
	Chemical coupling		
	Impact resistance, good		
	Good creep resistance		
	Low temperature impact resistance		
Uses	Application in Automobile Field		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PP		
Physical	Nominal Value	Unit	Test Method
Density	1.03	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4300	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	76.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.5	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	4400	MPa	ISO 178
Flexural Stress (23°C)	124	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	20	kJ/m ²	ISO 179/1eA
Injection	Nominal Value	Unit	
Drying Temperature	90.0 - 100	°C	

Drying Time	4.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	210 - 230	°C
Middle Temperature	230 - 240	°C
Front Temperature	240 - 250	°C
Nozzle Temperature	240 - 250	°C
Processing (Melt) Temp	210 - 270	°C
Mold Temperature	30.0 - 70.0	°C
Injection Pressure	60.0 - 120	MPa
Injection Rate	Slow	
Holding Pressure	40.0 - 80.0	MPa
Back Pressure	0.00 - 3.00	MPa

Injection instructions

Manifold Temperature: 210 to 270°C Zone 4 Temperature: 250°C Feed Temperature: 20 to 50°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

