# Sumikon® PM-TX210

### Phenolic

#### SBHPP

#### Message:

SUMIKON PM-TX210 is a Heat dissipative themoset molding compounds, Non-electrical insulative based on Phenolic polymer. It is supplied in the form of Granular/Molding Powder for Molding.

General Information				
Filler / Reinforcement	Inorganic filler			
Appearance	Black			
Forms	Powder			
	Particles			

Processing Method	Resin transfer molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.73	g/cm³	JIS K6911
Molding Shrinkage - Flow	0.30	%	JIS K6911
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	12500	MPa	JIS K6911
Flexural Strength	90.0	MPa	JIS K6911
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.3	kJ/m²	JIS K6911
Thermal	Nominal Value	Unit	
Thermal Conductivity	0.90	W/m/K	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

