

# LNP™ THERMOCOMP™ PF00C compound

Polyamide 6  
SABIC Innovative Plastics

Message:

LNP THERMOCOMP PF00C is a compound based on Nylon 6 resin containing 60% Glass Fiber.  
Also known as: LNP\* THERMOCOMP\* Compound PF-100-12  
Product reorder name: PF00C

General Information			
UL YellowCard	E121562-101344699		
Filler / Reinforcement	Glass Fiber,60% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.71	g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup>	22400	MPa	ASTM D638
Tensile Strength (Break)	211	MPa	ASTM D638
Tensile Elongation (Break)	2.4	%	ASTM D638
Flexural Modulus	19400	MPa	ASTM D790
Flexural Strength	365	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	170	J/m	ASTM D256
Unnotched Izod Impact (23°C)	1200	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	211	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	249 to 260	°C	
Middle Temperature	266 to 277	°C	
Front Temperature	277 to 288	°C	
Processing (Melt) Temp	266 to 277	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

