

IDI BMC B30 (Glass Content 25%)

Thermoset, Unspecified

IDI Composites International

Message:

PRODUCT SERIES: B30 SERIES BMC

PRODUCT DESCRIPTION: LOW PROFILE AUTOMOTIVE GRADE

Low shrink composite materials. Well suited for applications requiring shrink <0.1%.

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Features	Low Shrinkage		
Uses	Automotive Applications		
Forms	BMC - Bulk Molding Compound		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.80 to 2.00	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.0 to 0.10	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.10 to 0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Barcol Hardness	30 to 60		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	48.3	MPa	ASTM D638
Flexural Strength	82.7	MPa	ASTM D790
Compressive Strength	131	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	320	J/m	ASTM D256
Unnotched Izod Impact	530	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	> 204	°C	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Burning Rate	17	mm/min	ASTM D635

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT