# TOPAS® 8007D-61

## Cyclic Olefin Copolymer

### Topas Advanced Polymers, Inc.

#### Message:

Product Description

TOPAS 8007D-61 is an externally lubricated version of our 8007 series of injection molding resins, targeting injection blow molding (IBM) and injection stretch blow molding (ISBM) applications. Like the rest of the 8007 series, 8007D-61 is a glass-clear amorphous polymer with outstanding moisture barrier, chemical resistance, high purity and a non-reactive surface making it an excellent choice for healthcare and food products. Lower leachables and extractables of TOPAS COC preserve food and drug stability and quality. It is a non-polar substrate that does not promote adsorption, denaturation, aggregation, or precipitation like glass can. Analytical results are more accurate with pure TOPAS COC in contact with sensitive chemistries. Moisture-sensitive food, healthcare and consumer products stay fresh longer.

Selected Applications Drug delivery Prefilled syringes, vials, cartridges Bottles and tubes Surgical instruments IV containers and components Labware Food packaging Healthcare and food contact Leading Attributes Low leachables & extractables, low water transmission Non-ionic, does not promote adsorption like glass Minimally reactive Chemically resistant to alcohol, acetone, and acrylates Transparent, withstands EtO and gamma sterilization Temperature resistance, clarity and purity Not manufactured with BPA, phthalates, or halogens Broad regulatory compliance Related Grades for Injection Molding, Healthcare, Optics and Diagnostics TOPAS 8007S-04 - standard grade, appropriate for most applications

TOPAS 8007X10 - our highest ultraviolet (UV) transmission grade

#### General Information

Additive	Lubricant
Features	High purity
	Low extract
	Moisture proof
	Radiation disinfection
	Copolymer
	Ethylene oxide disinfection
	Good chemical resistance
	Alcohol resistance
	Heat resistance, high
	Definition, high
	Lubrication
	Compliance of Food Exposure
	BPA-free
	Halogen-free

Uses	Pipe fittings				
	Bottle				
	Laboratory apparatus Food packaging Surgical instruments Drug packaging Medical/nursing supplies				
Agency Ratings	DMF 12132				
	FDA FCN 405				
	Europe 10/1/2011 12:00:00 AM				
Appearance	Clear/transparent				
Forms	Particle				
Processing Method	Injection Stretch Blow Molding				
	Injection blowing molding				
	Injection molding				
Physical	Nominal Value	Unit	Test Method		
Density	1.02	g/cm <sup>3</sup>	ISO 1183		
Processing Method Physical Density	Injection Stretch Blow Molding Injection blowing molding Injection molding Nominal Value 1.02	Unit g/cm <sup>3</sup>	Test Method ISO 1183		

Melt Mass-Flow Rate (MFR) (260°C/2.16 kg)	29	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (260°C/2 16			
kg)	32.0	cm³/10min	ISO 1133
Molding Shrinkage <sup>1</sup>	0.10 - 0.30	%	Internal method
Water Absorption (Saturation, 23°C)	0.010	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	63.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	4.5	%	ISO 527-2/1A/50
Films	Nominal Value	Unit	Test Method
Water Vapor Transmission Rate (23°C, 85%			
RH)	0.025	g·mm/m²/atm/24 hr	DIN 53122
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	20	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa,			
Heat Deflection Temperature (0.45 MPa, Unannealed)	75.0	°C	ISO 75-2/B
Heat Deflection Temperature (0.45 MPa, Unannealed) Glass Transition Temperature	75.0 78.0	°C °C	ISO 75-2/B ISO 11357-2
Heat Deflection Temperature (0.45 MPa, Unannealed) Glass Transition Temperature Vicat Softening Temperature	75.0 78.0 80.0	°C ℃	ISO 75-2/B ISO 11357-2 ISO 306/B50
Heat Deflection Temperature (0.45 MPa, Unannealed) Glass Transition Temperature Vicat Softening Temperature Electrical	75.0 78.0 80.0 Nominal Value	°C ℃ ℃ Unit	ISO 75-2/B ISO 11357-2 ISO 306/B50 Test Method

Volume Resistivity	> 1.0E+16	ohms·cm	IEC 60093
Relative Permittivity			IEC 60250
1 kHz	2.35		IEC 60250
10 kHz	2.35		IEC 60250
Comparative Tracking Index	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	НВ		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.530		ISO 489
Transmittance	91.0	%	ISO 13468-2
Injection	Nominal Value	Unit	
Drying Temperature	50.0	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	190 - 220	°C	
Middle Temperature	200 - 240	°C	
Front Temperature	220 - 250	°C	
Nozzle Temperature	220 - 250	°C	
Processing (Melt) Temp	190 - 250	°C	
Mold Temperature	40.0 - 70.0	°C	
Injection Pressure	50.0 - 110	MPa	
Injection Rate	Moderate-Fast		
Holding Pressure	30.0 - 60.0	MPa	
Back Pressure	< 15.2	MPa	
Screw Speed	50 - 200	rpm	
Injection instructions			

Feed temperature: <60°C (<140°F)Max. Residence Time: 10 minutes, reduce Tx = 170°C (338°F)Injection speed: 50 - 150 mm/sec (2.0 - 6.0 in/sec)Nozzle type: Free flow

NOTE

1.

Dependent on process conditions and part design.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

