Yuyao PA 011BG20

Polyamide 66/6 Copolymer

Yuyao Tenglong Plastics Co., Ltd.

Message:

Yuyao PA 011BG20 is a Polyamide 66/6 Copolymer (Nylon 66/6) product filled with 20% glass fiber. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PA 011BG20 include electrical/electronic applications, appliances, automotive and tools.

Characteristics include:

Flame Rated

Flame Retardant

Good Processability

General Information

Heat Resistant

High Strength

Filler / Reinforcement	Glass Fiber,20% Filler by We	Glass Fiber,20% Filler by Weight				
Additive	Flame Retardant					
Features	Flame Retardant					
	Good Electrical Properties					
	Good Processability					
	High Heat Resistance					
	High Strength					
Uses	Appliance Components					
	Automotive Under the Hood					
	Communication Applications					
	Computer Components					
	Connectors					
	Electrical Parts					
	Power/Other Tools					
Processing Method	Injection Molding					
Physical	Nominal Value	Unit	Test Method			
Specific Gravity	1.25	g/cm³	ASTM D792			
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955			
Mechanical	Nominal Value	Unit	Test Method			
Tensile Strength	130	МРа	ASTM D638			
Tensile Elongation (Break)	7.0	%	ASTM D638			
Flexural Modulus	4500	МРа	ASTM D790			
Flexural Strength	150	МРа	ASTM D790			
Impact	Nominal Value	Unit	Test Method			
Notched Izod Impact (Area)	7.50	kJ/m²	ASTM D256			
Thermal	Nominal Value	Unit	Test Method			

Deflection Temperature Under Load (1.8			
MPa, Unannealed)	180	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	НВ		
3.20 mm	НВ		
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 95.0	°C	
Drying Time	5.0 to 8.0	hr	
Processing (Melt) Temp	245 to 265	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	80.0 to 100	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

