

# RTP 1005 TFE 15 GRAY

Polybutylene Terephthalate

RTP Company

## Message:

Warning: The status of this material is 'Commercial: Limited Issue'

The data for this material has not been recently verified.

Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	PTFE lubricant (15%)		
Features	Lubrication		
RoHS Compliance	Contact manufacturer		
Appearance	Grey		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.67	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.20	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.070	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9650	MPa	ASTM D638
Tensile Strength	103	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	8960	MPa	ASTM D790
Flexural Strength	172	MPa	ASTM D790
Compressive Strength	89.6	MPa	ASTM D695
Coefficient of Friction (With Metal-Dynamic)	0.20		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	96	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	590	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	207	°C	ASTM D648
CLTE - Flow	2.3E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.22	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149

Dielectric Constant (1 MHz)	4.00		ASTM D150
Dissipation Factor (1 MHz)	0.015		ASTM D150
Arc Resistance	110	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94

#### Additional Information

The value listed as Flammability, UL 94, was tested in accordance with RTP test standards. Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 3mil/in. Tensile Elongation, ASTM D-638: 2-3% Wear Factor, K, ASTM D-3702: 20E-10in<sup>3</sup>/min/ft/lb/hr Coefficient of Friction, Dynamic, ASTM D-3702: 0.20 The wear factor and coefficient of friction were both tested on a Falex Model No.6 Wear Testing Machine at 50 FPM, 2000 PV, against C1018 steel of hardness 15-25 Rockwell C, 14-17 micro smoothness.

Injection	Nominal Value	Unit
Rear Temperature	232 - 271	°C
Middle Temperature	232 - 271	°C
Front Temperature	232 - 271	°C
Mold Temperature	37.8 - 121	°C
Injection Pressure	68.9 - 103	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

