

HiFill® PA6/6 GF25 HS L

Polyamide 66
Techmer Engineered Solutions

Message:

HiFill®PA6/6 GF25 HS L is a polyamide 66 (nylon 66) product that contains a glass fiber reinforced material. It can be processed by injection molding and is available in North America.

Features include:

heat stabilizer

Lubrication

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Additive	heat stabilizer		
	Lubricant		
Features	Thermal Stability		
	Lubrication		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Water Absorption (24 hr)	1.8	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	165	MPa	ASTM D638
Tensile Elongation (Break)	3.5	%	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Flexural Strength	214	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	85	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	255	°C	ASTM D648
1.8 MPa, not annealed	250	°C	ASTM D648
CLTE - Flow	2.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257

Dielectric Strength ¹	19	kV/mm	ASTM D149
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.12	%	
Rear Temperature	282 - 293	°C	
Middle Temperature	288 - 299	°C	
Front Temperature	277 - 288	°C	
Nozzle Temperature	282 - 293	°C	
Processing (Melt) Temp	282 - 304	°C	
Mold Temperature	54.4 - 93.3	°C	
Injection Rate	Moderate-Fast		
Back Pressure	0.345 - 0.689	MPa	
Injection instructions			
Screw Speed: MediumRecommendations for Molding and Tool Conditions: Well ventedMoisture Content, as received: Product is packaged at 0.2% or less.Recomended Max Moisture: 0.12% down to 0.08%			
NOTE			

1. Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT