

EPOPLEN PP CFR 30 NC

Polypropylene

EPSAN Plastik SAN. ve TiC. A.S.

Message:

Polypropylene, reinforced with 30% of carbon fiber, suitable for injection moulding.
This product is available in black colours.

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 30% filler by weight		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.05 - 1.15	g/cm³	ISO 1183
Ash content-CARBON FIBER (550°C -10 min)	30.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	76 - 80		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1400 - 1900	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	35.0 - 70.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	4.0 - 8.0	%	ISO 527-2
Flexural Modulus (23°C)	1500 - 2000	MPa	ISO 178
Flexural Stress (23°C)	40.0 - 80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.0 - 11	kJ/m²	ISO 179/1eA
Notched Izod Impact (23°C)	7.0 - 11	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	155 - 170	°C	ISO 3146
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Additional Information			
TEST CONDITIONS: Laboratory conditions are 23 ±2°C and 45-55 % RH.			
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 - 4.0	hr	
Processing (Melt) Temp	220	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

