Plavis® C

Thermoplastic Polyimide

Comco Nylon GmbH

Message:

PLAVIS is a super engineering plastic. PLAVIS polyimide has a unique chemical structure with some of the highest properties available. Nitrogen bonded to 3 carbons is the critical part of the chain and imparts the plastic with remarkable features and benefits. DAELIM makes PLAVIS isostatic molded rods have uniform properties in all directions.

| General Information | |
|---------------------|-----------------------------------|
| Features | The degassing effect is low to no |
| | Conductivity |
| | Heat resistance, high |
| | Flame retardancy |

| Physical | Nominal Value | Unit | Test Method |
|----------------------------------------------------|---------------|--------|-------------|
| Specific Gravity | 1.44 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness (M-Scale, Compression Molded) | 90 - 105 | | ASTM D785 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ | | | ASTM D1708 |
| Fracture, 23°C | 83.3 | MPa | ASTM D1708 |
| Fracture, 260°C | 39.2 | MPa | ASTM D1708 |
| Tensile Elongation ² | | | ASTM D1708 |
| Fracture, 23°C | 7.0 | % | ASTM D1708 |
| Fracture, 260°C | 6.0 | % | ASTM D1708 |
| Flexural Modulus (23°C, Compression Molded) | 3430 | MPa | ASTM D790 |
| Flexural Strength (23°C, Compression | | | |
| Molded) | 108 | MPa | ASTM D790 |
| Compressive Modulus ³ | 2450 | MPa | ASTM D695 |
| Compressive Strength ⁴ | | | ASTM D695 |
| 1% strain, 23°C | 24.5 | MPa | ASTM D695 |
| 10% strain, 23°C | 147 | MPa | ASTM D695 |
| Coefficient of Friction ⁵ | 0.32 | | |
| Wear Rate | 33 | mm/sec | |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, Compression Molded) | 49 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | |
| Thermal Conductivity ⁶ (25°C) | 0.37 | W/m/K | |
| Electrical | Nominal Value | Unit | Test Method |

| Surface Resistivity ⁷ | 1.0 - 1.0E+3 | ohms | ASTM D257 |
|----------------------------------|--------------------|------|-----------|
| NOTE | | | |
| 1. | Compression Molded | | |
| 2. | Compression Molded | | |
| 3. | Compression Molded | | |
| 4. | Compression Molded | | |
| 5. | Compression Molded | | |
| 6. | Compression Molded | | |
| 7. | Compression Molded | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

