

TRIBOCOMP® PEEK CF30 TS0

Polyetheretherketone
EPIC Polymers

Message:

TRIBOCOMP® PEEK CF30 TS0 is a polyetheretherketone (PEEK) product, which contains 15% ptfe fiber and 20% carbon fiber reinforced materials. It is available in Europe. The main characteristics are: lubrication.

General Information			
Filler / Reinforcement	PTFE fiber, 15% filler by weight		
	Carbon fiber reinforced material, 20% filler by weight		
Additive	PTFE lubricant (15%)		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.54	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.20	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	17500	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	175	MPa	ISO 527-2
Tensile Strain (Break)	1.5	%	ISO 527-2
Flexural Modulus (23°C)	15500	MPa	ISO 178
Flexural Stress (23°C)	250	MPa	ISO 178
Coefficient of Friction			ASTM D3702
Dynamic	0.19		ASTM D3702
Static	0.18		ASTM D3702
Wear Factor	15.0		ASTM D3702
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	40	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	320	°C	ISO 75-2/B
1.8 MPa, not annealed	315	°C	ISO 75-2/A
CLTE - Flow (23°C)	1.5E-5	cm/cm/°C	ISO 7991
Thermal Conductivity	0.60	W/m/K	ISO 22007
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2	ohms	ASTM D257
Additional Information			
The value listed as Molding Shrinkage ISO 294-4, was tested in accordance with S.O.P. methods.			

Injection	Nominal Value	Unit
Drying Temperature	150	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	340 - 360	°C
Middle Temperature	360 - 380	°C
Front Temperature	380 - 390	°C
Nozzle Temperature	380 - 390	°C
Mold Temperature	160 - 200	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

