SCLAIR® 2908C

High Density Polyethylene

NOVA Chemicals

Message:

 ${\tt SCLAIR} @ \ 2908C \ is \ a \ {\tt High \ Density \ Polyethylene \ material}. \ It \ is \ available \ in \ North \ America \ for \ injection \ molding.$

Important attributes of SCLAIR® 2908C are:

Antioxidant

Food Contact Acceptable

Good Toughness

High Stiffness

Impact Resistant

Typical applications include:

Containers

Food Contact Applications

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Food Contact Acceptable		
	Good Impact Resistance		
	Good Toughness		
	High Density		
	High Stiffness		
Uses	Crates		
Agency Ratings	FDA 21 CFR 177.1520(c) 2.2		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.961	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	10	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (100% Igepal, F50)	< 10.0	hr	ASTM D1693A
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	66		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	29.0	MPa	ASTM D638
Tensile Elongation ² (Break)	900	%	ASTM D638
Flexural Modulus	1280	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	129	°C	ASTM D1525
NOTE			
1.	50 mm/min		

2. 50 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

