

Celanex® 2002-2

Polybutylene Terephthalate

Celanese Corporation

Message:

Celanex 2002-2 is a general purpose, unreinforced polybutylene terephthalate with a good balance of mechanical properties and processability. Celanex 2002-2 is a medium flow material that contains an internal lubricant.

General Information			
UL YellowCard	E42337-234643	E45575-239360	
Additive	Lubricant		
Features	Workability, good		
	Medium liquidity		
	Lubrication		
	General		
Uses	General		
RoHS Compliance	Contact manufacturer		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
	Shear Stress vs. Shear Rate (ISO 11403-1)		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)	20	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	20.0	cm ³ /10min	ISO 1133
Molding Shrinkage			
Flow	1.8 - 2.0	%	ASTM D955
Flow direction	1.8 - 2.0	%	ISO 294-4

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	78		ISO 2039-2

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-40°C	3100	MPa	ASTM D638
23°C	3170	MPa	ASTM D638
80°C	469	MPa	ASTM D638
121°C	296	MPa	ASTM D638
--	2600	MPa	ISO 527-2/1A/1
Tensile Strength			
Yield, -40°C	101	MPa	ASTM D638
Yield, 0°C	75.8	MPa	ASTM D638

Yield, 23°C	55.8	MPa	ASTM D638
Yield, 80°C	24.8	MPa	ASTM D638
Yield, 121°C	17.9	MPa	ASTM D638
Yield	60.0	MPa	ISO 527-2/1A/50
Fracture, 23°C	55.8	MPa	ASTM D638
Fracture	60.0	MPa	ISO 527-2/1A/50
50% strain	30.0	MPa	ISO 527-2/1A/50
Tensile Elongation			
Yield, -40°C	7.2	%	ASTM D638
Yield, 0°C	4.4	%	ASTM D638
Yield, 23°C	3.2	%	ASTM D638
Yield, 80°C	17	%	ASTM D638
Yield, 121°C	23	%	ASTM D638
Yield	4.0	%	ISO 527-2/1A/50
Fracture, 23°C	200	%	ASTM D638
Nominal Tensile Strain at Break	> 50	%	ISO 527-2/1A/50
Flexural Modulus (23°C)	2500	MPa	ISO 178
Flexural Stress (23°C)	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	6.0	kJ/m ²	ISO 179/1eA
23°C	6.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	190	kJ/m ²	ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact (23°C)	5.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	150	°C	ISO 75-2/B
0.45 MPa, annealed	160	°C	ASTM D648
1.8 MPa, not annealed	55.0	°C	ASTM D648, ISO 75-2/A
Glass Transition Temperature ¹	60.0	°C	ISO 11357-2
Vicat Softening Temperature	190	°C	ISO 306/B50
Melting Temperature ²	225	°C	ISO 11357-3, ASTM D3418
Linear thermal expansion coefficient			ISO 11359-2
Flow	1.1E-4	cm/cm/°C	ISO 11359-2
Lateral	1.3E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity			
--	1.0E+16	ohms · cm	ASTM D257
--	1.0E+15	ohms · cm	IEC 60093

Dielectric Strength			
-- ³	17	kV/mm	ASTM D149
--	23	kV/mm	IEC 60243-1
Dielectric Constant			
1 MHz	3.20		ASTM D150
100 Hz	4.00		IEC 60250
1 MHz	3.50		IEC 60250
Dissipation Factor			
100 Hz	1.4E-3		IEC 60250
1 MHz	0.022		IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.710 mm)	HB		UL 94
Oxygen Index	22	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	120 - 130	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Max Regrind	25	%	
Hopper Temperature	20.0 - 50.0	°C	
Rear Temperature	230 - 240	°C	
Middle Temperature	235 - 250	°C	
Front Temperature	235 - 250	°C	
Nozzle Temperature	250 - 260	°C	
Processing (Melt) Temp	235 - 260	°C	
Mold Temperature	65.0 - 93.0	°C	
Injection Rate	Moderate-Fast		
Back Pressure	0.00 - 0.345	MPa	
Injection instructions			
Manifold Temperature: 250 to 260°CZone 4 Temperature: 240 to 260°CFeed Temperature: 230 to 240°C			
NOTE			
1.	10°C/min		
2.	10°C/min		
3.	Method A (short time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

