

# Mar-Bal MB1000-PC

Thermoplastic Polyester

Mar-Bal, Inc.

Message:

A general purpose material that is easily customized. Designed for Powder Coating and Electrostatic painting.

General Information			
UL YellowCard	E80533-250691		
Features	General Purpose		
Uses	Coating Applications		
	General Purpose		
	Paint		
UL File Number	E80533		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.90 to 2.09	g/cm <sup>3</sup>	ASTM D792
Bulk Factor	1.0		ASTM D1895
Molding Shrinkage - Flow	0.0 to 0.10	%	ASTM D955
Water Absorption (24 hr)	0.17	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Barcol Hardness	60 to 65		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	31.0 to 37.9	MPa	ASTM D638
Flexural Modulus	8960 to 11000	MPa	ASTM D790
Flexural Strength	68.9 to 82.7	MPa	ASTM D790
Compressive Modulus	379000 to 393000	MPa	ASTM D695
Compressive Strength	138 to 152	MPa	ASTM D695
Shear Strength	68.9 to 75.8	MPa	ASTM D732
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	270 to 320	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	> 260	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Arc Resistance	> 180	sec	ASTM D495
Inclined-Plane Tracking	> 500	min	ASTM D2303
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT