

# Supol HT950E

Polyolefin  
LyondellBasell Industries

Message:

SUPOL HT950E is a high melt flow, mineral filled, UV resistant polypropylene copolymer compound for injection moulding. it has been designed for automotive interior applications. The grade is available in custom colours.

| General Information                       |                          |                   |             |
|---|--------------------------|-------------------|-------------|
| Filler / Reinforcement                    | Mineral                  |                   |             |
| Features                                  | Copolymer                |                   |             |
|   | Good Flow                |                   |             |
|   | Good Stiffness           |                   |             |
|   | Good UV Resistance       |                   |             |
| Uses                                      | Automotive Interior Trim |                   |             |
| Appearance                                | Colors Available         |                   |             |
| Forms                                     | Pellets                  |                   |             |
| Processing Method                         | Injection Molding        |                   |             |
| Physical                                  | Nominal Value            | Unit              | Test Method |
| Density                                   | 1.05                     | g/cm <sup>3</sup> | ISO 1183/A  |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 18                       | g/10 min          | ISO 1133    |
| Mechanical                                | Nominal Value            | Unit              | Test Method |
| Flexural Modulus                          | 2800                     | MPa               | ISO 178     |
| Impact                                    | Nominal Value            | Unit              | Test Method |
| Notched Izod Impact Strength (23°C)       | 4.0                      | kJ/m <sup>2</sup> | ISO 180/1A  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT