

Diakon® Frost 952 70

Polymethyl Methacrylate Acrylic

Lucite International Inc.

Message:

Diakon® Frost 952 70 is a polymethyl methacrylate-acrylic material. This product is available in Europe and is processed by extrusion. Diakon® The main characteristics of Frost 952 70 are: flame retardant/rated flame.

General Information			
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	1.5	g/10 min	ISO 1133
Water Absorption (Equilibrium, 23°C, 50% RH)	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ISO 2039-2
Ball Indentation Hardness (H 961/30)	170	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	72.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.4	%	ISO 527-2
Flexural Modulus	3200	MPa	ISO 178
Flexural Stress	120	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	22	kJ/m ²	ISO 179/1eU
Notched Izod Impact	1.6	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	99.0	°C	ISO 75-2/B
1.8 MPa, not annealed	95.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	108	°C	ISO 306/A
--	101	°C	ISO 306/B
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Glow Wire Ignition Temperature	650	°C	IEC 60695-2-13
Optical	Nominal Value	Unit	Test Method
Transmittance	80.5	%	ASTM D1003
Haze	98	%	ASTM D1003
Extrusion	Nominal Value	Unit	

Drying Temperature	80.0	°C
Drying Time	3.0 - 4.0	hr
Hopper Temperature	50.0 - 80.0	°C
Cylinder Zone 1 Temp.	160 - 240	°C
Cylinder Zone 2 Temp.	180 - 250	°C
Cylinder Zone 3 Temp.	200 - 250	°C
Cylinder Zone 4 Temp.	220 - 260	°C
Adapter Temperature	210 - 270	°C
Die Temperature	210 - 270	°C
Extrusion instructions		

Vent Zone: 220 to 270°C Zone 6: 220 to 270°C Zone 7: 210 to 270°C Zone 8: 210 to 270°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

