

Durethan® BKV 115 H3.0 DUS008 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 15% glass fibers, injection molding, improved impact strength, heat-aging stabilized

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 15% filler by weight		
Additive		heat stabilizer		
Features		Impact resistance, good		
		Thermal Stability		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.23	--	g/cm ³	ISO 1183
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	5600	2800	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	115	65.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	4.0	12	%	ISO 527-2/5
Flexural Modulus ¹ (23°C)	4900	2500	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	165	70.0	MPa	ISO 178/A
23°C ²	185	95.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ³ (23°C)	5.0	8.0	%	ISO 178/A
ISO Shortname	PA 6-HI, GHR, 14-060, GF15	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	--	kJ/m ²	ISO 179/1eA
23°C	< 10	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	50	--	kJ/m ²	ISO 179/1eU
23°C	65	80	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	215	--	°C	ISO 75-2/B

1.8 MPa, not annealed	195	--	°C	ISO 75-2/A
Melting Temperature ⁴	220	--	°C	ISO 11357-3
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	260 - 290		°C	
Mold Temperature	80.0 - 100		°C	
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			
3.	2 mm/min			
4.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

