

# K-vinyl 20 A 74

Polyvinyl Chloride  
Technovinyl Polymers India Ltd.

Message:

K-vinyl 20 A 74 is a Polyvinyl Chloride material. It is available in Africa & Middle East for extrusion.  
Important attributes of K-vinyl 20 A 74 are:  
Low to No Odor/Taste  
Clarity  
Non-Toxic  
Stabilized  
Typical applications include:  
Hose/Tubing  
Medical/Healthcare

General Information			
Additive	Calcium-Zinc Stabilizer		
Features	Good Color Stability		
	Good Stability		
	High Clarity		
	Kink Resistant		
	Low to No Migration		
	Low to No Odor		
	Low to No Taste		
	Non-Toxic		
Uses	Medical/Healthcare Applications		
	Tubing		
Appearance	Clear/Transparent		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	69 to 79		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	13.0	MPa	ASTM D412
Tensile Elongation (Break)	240	%	ASTM D412
Thermal	Nominal Value	Unit	
Thermal Stability (> 200°C)	15	min	
Volatile Loss - 3 hrs (130°C)	0.60	%	
Extrusion	Nominal Value	Unit	
Melt Temperature	145 to 180	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

