

Propylplus 707E

Polypropylene
Fainplast Compounds S.r.l

Message:

Propylplus is a range of polypropylene and halogen free compounds specially designed for those applications requiring superior thermo-mechanical properties, outstanding heat resistance and high electrical properties.

They can be used as primary insulation on multimedia, telecom, instrumentation wires, optical fiber cables and other applications where extremely thin wall thickness must comply with high performing properties.

General Information			
Features	Good Electrical Properties		
	High Heat Resistance		
Uses	Insulation		
	Wire & Cable Applications		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (180°C/5.0 kg)	8.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	61		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	28.0	MPa	ISO 527-2/50
Tensile Strain (Break)	750	%	ISO 527-2/50
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	150	°C	ISO 306/A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (20°C)	> 1.0E+17	ohms · cm	ASTM D257
Dielectric Constant (1 MHz)	2.26		
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	180	°C	
Cylinder Zone 2 Temp.	190	°C	
Cylinder Zone 3 Temp.	200	°C	
Cylinder Zone 4 Temp.	210	°C	
Head Temperature	230	°C	
Die Temperature	240	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

