

RAMTAL PM1109

Acetal (POM) Copolymer
Polyram Ram-On Industries

Message:
COLORED GENERAL PURPOSE POLYACETAL COPOLYMER FOR INJECTION MUOLDING APPLICATIONS.

General Information			
Features	General		
Uses	General		
RoHS Compliance	RoHS compliance		
Appearance	Available colors		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow	1.8 - 2.2	%	ASTM D955
--	1.8 - 2.2	%	ISO 2577
Water Absorption			
Saturation	0.22	%	ASTM D570
Saturated, 23°C	0.22	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class r	80		ASTM D785
R scale	80		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	60.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation			ASTM D638, ISO 527-2
Yield	35	%	ASTM D638, ISO 527-2
Fracture	15	%	ASTM D638, ISO 527-2
Flexural Modulus	2600	MPa	ASTM D790, ISO 178
Flexural Strength	80.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	65	J/m	ASTM D256
23°C	6.5	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, not annealed	160	°C	ASTM D648, ISO 75-2/B

1.8 MPa, not annealed	110	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	134	°C	ASTM D1525, ISO 306
Melting Temperature	165	°C	ISO 11357-3, ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+18	ohms·cm	IEC 60093
Dielectric Strength	24	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	3.80		IEC 60250
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	175 - 200	°C	
Middle Temperature	180 - 205	°C	
Front Temperature	190 - 210	°C	
Mold Temperature	60.0 - 110	°C	
Injection Pressure	70.0 - 105	MPa	
Holding Pressure	35.0 - 85.0	MPa	
Back Pressure	0.350 - 0.700	MPa	
Screw Speed	60 - 90	rpm	
Injection instructions			

Fill Speed: 25 to 50 mm/sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT