

RTP ESD C 480 HI

High Impact Polystyrene

RTP Company

Message:

Impact Modified - Carbon Fiber - ESD Protection - Electrically Conductive

General Information			
Filler / Reinforcement	Carbon Fiber		
Additive	Impact Modifier		
Features	Electrically Conductive		
	ESD Protection		
	Impact Modified		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.10 to 0.20	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7580	MPa	ASTM D638
Tensile Strength	48.3	MPa	ASTM D638
Tensile Elongation (Yield)	1.0 to 2.0	%	ASTM D638
Flexural Modulus	6210	MPa	ASTM D790
Flexural Strength	62.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	160	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			
--	< 1.0E+6	ohms	ASTM D257
--	< 1.0E+5	ohms	ESD STM11.11
Volume Resistivity	< 1.0E+3	ohms · cm	ASTM D257
Static Decay ¹	< 2.0	sec	FTMS 101C 4046.1
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	210 to 249	°C	
Mold Temperature	37.8 to 65.6	°C	
Injection Pressure	68.9 to 103	MPa	
NOTE			

1.

MIL-PRF-81705D, 5kV to 50 V, 12%
RH

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

