

HiFill FR® ABS GF20 FR RD073

Acrylonitrile Butadiene Styrene

Techmer Engineered Solutions

Message:

HiFill FR® ABS GF20 FR RD073 is an Acrylonitrile Butadiene Styrene (ABS) product filled with 20% glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

Flame Rated

Flame Retardant

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Flame Retardant		
Appearance	Colors Available		
	Red		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.20	%	ASTM D955
Water Absorption (24 hr)	0.16	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	124		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	60.0	MPa	ASTM D638
Tensile Elongation (Break)	3.0 to 4.0	%	ASTM D638
Flexural Modulus	5170	MPa	ASTM D790
Flexural Strength	82.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	64	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	320	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	98.9	°C	
1.8 MPa, Unannealed	93.3	°C	
CLTE - Flow	4.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength ¹	18	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method

Flame Rating (1.50 mm)	V-0	UL 94
Injection	Nominal Value	Unit
Drying Temperature	71.1 to 82.2	°C
Drying Time	2.0 to 16	hr
Rear Temperature	210 to 227	°C
Middle Temperature	216 to 232	°C
Front Temperature	204 to 216	°C
Nozzle Temperature	193 to 216	°C
Processing (Melt) Temp	227 to 254	°C
Mold Temperature	65.6 to 82.2	°C
NOTE		
1.	Method A (Short-Time)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT