

Raditer® B RV300

Polybutylene Terephthalate

Radici Plastics

Message:

PBT 30% Glass Fiber reinforced injection moulding grade. High stiffness and good dimensional stability. Natural colour

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Good dimensional stability		
	Rigid, good		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cm ³	ISO 1183
Water Absorption			ISO 62
Saturated, 23°C	0.30	%	ISO 62
Equilibrium, 23°C, 50% RH	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10200	MPa	ISO 527-2
Tensile Stress (Break)	130	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/eA
-30°C	9.4	kJ/m ²	ISO 179/eA
23°C	9.4	kJ/m ²	ISO 179/eA
Charpy Unnotched Impact Strength			ISO 179/eU
-30°C	61	kJ/m ²	ISO 179/eU
23°C	66	kJ/m ²	ISO 179/eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	215	°C	ISO 75-2/Bf
1.8 MPa, not annealed	205	°C	ISO 75-2/Af
Vicat Softening Temperature	210	°C	ISO 306/B50
Melting Temperature (DSC)	225	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index	450	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method

Flame Rating		UL 94
0.800 mm	HB	UL 94
1.60 mm	HB	UL 94

Additional Information

The value listed as Melting Temperature, ISO 3146, was tested in accordance with ISO 11357-1-3 at a heating rate of 10°C/min.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

