TECOLITE KM-757(J)

Phenolic

KYOCERA Chemical Corporation

Message:

Provides wide range moldability and Superior cost performance and Expands the possibility of design.

Kyocera Chemical's Phenolic Molding Compounds "TECOLITE" can possible to high cycle molding and excellent stability within a cylinder. Moreover, "TECOLITE" have a wide molding condition and can be found out easily. In the parts, "TECOLITE" have small mold shrinkage factor therefore it is suitable for precision parts. It is especially the best for mass-production parts, such as a non-fuse breaker, various electric parts, and kitchen parts, etc.

| General Information | | | |
|--------------------------------|------------------------------------|-------|-------------|
| Features | Fast Cure | | |
| | Low Shrinkage | | |
| Uses | Electrical/Electronic Applications | | |
| | Kitchenware | | |
| Appearance | Black | | |
| Physical | Nominal Value | Unit | |
| Specific Gravity | 1.40 | g/cm³ | |
| Molding Shrinkage | | | |
| Flow ¹ | 1.2 to 1.4 | % | |
| Flow ² | 0.70 to 0.90 | % | |
| Across Flow ³ | 0.90 to 1.1 | % | |
| Water Absorption (Equilibrium) | < 0.35 | % | |
| Mechanical | Nominal Value | Unit | |
| Flexural Strength | 78.0 to 98.0 | MPa | |
| Compressive Strength | 216 to 245 | MPa | |
| Thermal | Nominal Value | Unit | |
| Heat Deflection Temperature | 170 | °C | |
| Insulation Resistance | | | |
| After Boiling | 1.0E+8 to 1.0E+9 | ohms | |
| As Molded | 1.0E+9 to 1.0E+11 | ohms | |
| Electrical | Nominal Value | Unit | Test Method |
| Dielectric Strength | > 8.0 | kV/mm | |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating (0.710 mm) | НВ | | UL 94 |
| NOTE | | | |
| 1. | Injection Molding | | |
| 2. | Compression Molding | | |
| 3. | Injection Molding | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

