

Novalloy-B B14MO

Acrylonitrile Butadiene Styrene + PBT

Daicel Polymer Ltd.

Message:

Novalloy-B B14MO is an Acrylonitrile Butadiene Styrene + PBT (ABS+PBT) material. It is available in Asia Pacific.

General Information			
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.60 to 0.90	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	40.0	MPa	ISO 527-2
Flexural Modulus	1900	MPa	ISO 178
Flexural Stress	60.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	50	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	80.0	°C	ISO 75-2/A
CLTE - Flow	1.0E-4	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 120	°C	
Drying Time	3.0 to 5.0	hr	
Rear Temperature	190 to 230	°C	
Middle Temperature	220 to 240	°C	
Front Temperature	240 to 250	°C	
Nozzle Temperature	230 to 250	°C	
Mold Temperature	60.0 to 80.0	°C	
Back Pressure	5.00 to 20.0	MPa	
Screw Speed	50 to 90	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

