

Polytech & Net XP 9200EN

Metallocene Linear Low Density Polyethylene

Polytech & Net GmbH

Message:

Lamination Film, Agricultural Film, High Strength Film, Stretch Hood film

General Information	
Uses	Agricultural Applications
	Film
	Laminates
Agency Ratings	EU 2002/72/EC
	FDA 21 CFR 177.1520

Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (F50)	400	hr	ASTM D1693

Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882
MD : Break	56.9	MPa	
TD : Break	45.1	MPa	
Tensile Elongation			ASTM D882
MD : Break	580	%	
TD : Break	620	%	
Dart Drop Impact	700	g	ASTM D1709B
Elmendorf Tear Strength			ASTM D1004
MD	120	g	
TD	130	g	
Seal Initiation Temperature ¹	95.0	°C	

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	106	°C	ASTM D1525
Peak Melting Temperature	116	°C	ASTM D3418

Optical	Nominal Value	Unit	Test Method
Gloss (45°)	87		ASTM D2457
Haze	12	%	ASTM D1003

NOTE	
1.	HGT, 2.8kg, 0.5 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

