

NEXUS ABS ABSLG5035

Acrylonitrile Butadiene Styrene

Nexus Resin Group, LLC.

Message:

Molding Grade ABS, Low Gloss

General Information			
Features	Low Gloss		
UL File Number	E205256		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ASTM D638
Tensile Strength (Yield)	40.0	MPa	ASTM D638
Flexural Modulus	2070	MPa	ASTM D790
Flexural Strength (Yield)	58.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	190	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	76.7	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value		Test Method
Gardner Gloss (60°)	< 60		ASTM D523
Injection	Nominal Value	Unit	
Drying Temperature	82.2 to 93.3	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.15	%	
Rear Temperature	188 to 218	°C	
Middle Temperature	204 to 232	°C	
Front Temperature	218 to 246	°C	
Nozzle Temperature	218 to 274	°C	
Processing (Melt) Temp	218 to 274	°C	
Mold Temperature	48.9 to 76.7	°C	
Back Pressure	0.172 to 0.689	MPa	
Screw Speed	25 to 75	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

