

Optema™ TC 120 ExCo

Ethylene Methyl Acrylate Copolymer Resin

ExxonMobil Chemical

Message:

Optema TC 120 is an ethylene-methyl acrylate copolymer for extrusion coating, coextrusion coating and extrusion compounding requiring good adhesion between polyethylene, polypropylene, nylon, polydichloroethylene or other substrates. It can well balance the adhesion on the substrate and the interlayer adhesion with coextruded low density polyethylene and ethylene vinyl acetate copolymer. It is an excellent heat sealing layer in co-extrusion and extrusion coating, but may require additional additives or process corrections to avoid cooling roller adhesion. Processing conditions: Excellent extrusion coating effect can be obtained in the temperature range of 260°C to 300°C (500 ° F-572 °F). It is recommended that the processing temperature should not be higher than 32 0°C (608 °F). Optema EMA can be processed on traditional extrusion equipment for extrusion coating low density polyethylene. Its wide range of thermal stability provides a wide processing window. The nozzle of the extruder should be cooled by water to avoid bridging the feed port. Surface coating is recommended to use matte cold roll surface processing.

General Information			
Additive	heat stabilizer		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0	g/10 min	ASTM D1238
Methyl Acrylate Content	21.5	wt%	ExxonMobil Method
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	47.0	°C	ASTM D1525
Legal statement			
有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用			
Extrusion instructions			

Excellent results are obtained in extrusion coating at 260°C to 300°C (500°F - 572°F) temperature range. Processing temperatures above 320°C (608°F) are not recommended. Optema EMA can be processed on conventional extrusion equipment designed for extrusion coating LDPE. Their broad thermal stability range offers wide processing conditions window. Water cooling of extruder throat is preferred to avoid hopper bridging. Matte chill roll finishing is recommended for top coating.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT