

Ultramid® A3K FC Aqua UN

Polyamide 66

BASF Corporation

Message:

Ultramid® A3K FC Aqua UN is optimized for plastic parts, mandatory requiring material approvals for drinking water or direct food contact.

General Information				
Features		Compliance of Food Exposure		
Uses		Non-specific food applications		
		Potable water application		
Agency Ratings		ACS not rated		
		DVGW W270		
		EC 1907/2006 (REACH)		
		EC 2023/2006		
		FDA 21 CFR 177.1500		
		KTW not rated		
		NSF Not Rated		
		WRAS not rated		
		Europe 10/1/2011 12:00:00 AM		
RoHS Compliance		RoHS compliance		
Forms		Particle		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.13	--	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	115	--	cm ³ /10min	ISO 1133
Water Absorption				ISO 62
Saturated, 23°C	8.0 - 9.0	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.5 - 3.1	--	%	ISO 62
Viscosity Number (96% H2SO4)	150	--	cm ³ /g	ISO 307
Mold Shrinkage - constrained ¹	0.85	--	%	
Temperature index-at 50% loss of tensile strength				IEC 60216
-- ²	118	--	°C	IEC 60216
-- ³	101	--	°C	IEC 60216

Maximum operating temperature-short cycle operation	200	--	°C	
Automotive Materials (> 1.00 mm)	Pass	--		FMVSS 302
Screw Speed			mm/sec	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3100	1100	MPa	ISO 527-2
Tensile Stress (Yield)	85.0	50.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	5.0	20	%	ISO 527-2/50
Nominal Tensile Strain at Break	30	> 50	%	ISO 527-2/50
Tensile Creep Modulus ⁴ (1000 hr)	--	700	MPa	ISO 899-1
Flexural Modulus	2900	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	4.0	--	kJ/m ²	ISO 179/1eA
23°C	5.0	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break	No Break		ISO 179/1eU
Notched Izod Impact				ISO 180/A
-30°C	6.0	--	kJ/m ²	ISO 180/A
23°C	5.5 kJ/m ²	No Break		ISO 180/A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	220	--	°C	ISO 75-2/B
1.8 MPa, not annealed	75.0	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	ISO 11357-3
CLTE - Flow (23 to 80°C)	7.0E-5 - 1.0E-4	--	cm/cm/°C	ISO 11359-2
Specific Heat	1700	--	J/kg/°C	
Thermal Conductivity	0.33	--	W/m/K	DIN 52612
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Relative Permittivity (1 MHz)	3.20	5.00		IEC 60250
Dissipation Factor (1 MHz)	0.025	0.20		IEC 60250
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	V-2	--		UL 94
Injection	Dry	Unit		

Drying Temperature	80.0	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.15	%
Hopper Temperature	80.0	°C
Rear Temperature	290	°C
Middle Temperature	290	°C
Front Temperature	290	°C
Nozzle Temperature	290	°C
Processing (Melt) Temp	280 - 300	°C
Mold Temperature	60.0 - 80.0	°C

Injection instructions

Residence Time: <10 min.

NOTE

1. Test box with central gating, dimensions of base (107*47*1,5) mm, processing condition: TM = 290°C, TW = 60°C
2. 5000 h
3. 20000 h
4. strain <= 0.5%, 23°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT