Europrene® NEOCIS BR 60

High Cis Polybutadiene Rubber

Versalis S.p.A.

Message:

Europrene ® Neocis BR 60 is a solution high cis polybutadiene polymer produced with an organometallic neodymium catalyst at the Ravenna production facility in Italy.

A non-staining antioxidant is added during the production process.

Key Features

Europrene ® Neocis BR 60 is an elastomer characterised by an excellent resistance to abrasion, high resilience/ rebound, good resistance to fatigue cracking and crack growth.

Its low glass transition temperature provides enhanced low temperature performance compared to that of other general purpose rubbers. Europrene ® Neocis BR 60 exhibits improved mechanical and elastic properties compared to Europrene ® Neocis BR 40; nevertheless a loss of processability should be considered.

Main Applications

1.

Tyre tread and sidewall, camelback, conveyor belts, technical goods, hoses, golf balls.

| General Information | | | |
|---|---------------------------|----------|-----------------|
| Additive | Antioxidant | | |
| Features | Antioxidant | | |
| | Fatigue Resistant | | |
| | Good Abrasion Resistance | | |
| | Good Crack Resistance | | |
| | Low Temperature Resistant | | |
| | Resilient | | |
| | | | |
| Uses | Automotive Applications | | |
| | Belts/Belt Repair | | |
| | Conveyor Parts | | |
| | Hose | | |
| | Sporting Goods | | |
| | | | |
| Forms | Bale | | |
| Physical | Nominal Value | Unit | Test Method |
| Mooney Viscosity ¹ (ML 1+4, 100°C) | 63 | MU | ASTM D1646 |
| 1,4-cis Content | > 97.0 | wt% | Internal Method |
| Ash Content | < 0.5 | wt% | ASTM D5667 |
| Volatile Matter | < 0.75 | wt% | ASTM D5668 |
| NOTE | | | |
| | | <u> </u> | <u> </u> |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

unmassed

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

