

Escor™ 5000

Ethylene Acrylic Acid Copolymer Resin

ExxonMobil Chemical

Message:

Escor 5000 is mainly used for extrusion coating, coextrusion coating and extrusion compounding. It can be well bonded to polar substrates, aluminum foils, metal films, paper, steel and glass surfaces. Provides an excellent balance of adhesion to the surface of the substrate and interlayer adhesion to coextruded low density polyethylene and ethylene vinyl acetate. Excellent adhesive polymer in film.

General Information			
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.2	g/10 min	ASTM D1238
Acrylic Acid Content	6.0	wt%	ExxonMobil Method

Legal statement

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

Extrusion instructions

Excellent results are obtained in extrusion coating at 260°C - 280°C (500°F - 536°F) temperature range. Processing temperatures above 300°C (572°F) may cause resin degradation. To minimize corrosion risk, all exposed metal surfaces in the extruder and die should be made from corrosion resistant metals or nickel/chrome plated. ESCOR should be fed into the extruder after LDPE of a similar or higher melt index. Machines should always be completely purged with LDPE or a suitable cleaning compound before shutdown.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

