Hostacom PPU X9067HS G62514

Polypropylene Copolymer LyondellBasell Industries

Message:

Hostacom PPU X9067HS G62514 is an unfilled PP copolymer, with high melt flow rate, high toughness and increased stiffness. Please contact Lyondellbasell for shrinkage recommendations. The product is also available in other color matched, pellet form. This grade is delivered in G62514 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Features	Rigid, good		
	Copolymer		
	High liquidity		
	Good toughness		
Uses	Application in Automobile Field		
	Car interior equipment		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.910	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	13	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	26.0	MPa	ISO 527-2
Flexural Modulus ¹ (23°C)	1450	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	11	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	58.0	°C	ISO 75-2/A
Vicat Softening Temperature	147	°C	ISO 306/A
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

