

NEONIT® SK61 L5G

Epoxy; Epoxide

SBHPP

Message:

NEONIT® SK61 L5G is a long glass fiber reinforced epoxy molding compound with excellent long term property retention over a wide temperature range and climate conditions. It is particularly suited for over molding.

General Information	
Filler / Reinforcement	Long glass fiber
Uses	overmolding
Agency Ratings	EC 1907/2006 (REACH)
	EU 2002/96/EC (WEEE)
	EU 2006/122/EC
RoHS Compliance	RoHS compliance
Appearance	Dark gray
Forms	flake
Processing Method	Resin transfer molding
	Compression molding

Physical	Nominal Value	Unit	Test Method
Density	1.80	g/cm ³	ISO 1183
Apparent Density	0.65	g/cm ³	ISO 60
Molding Shrinkage	0.15	%	ISO 2577
Water Absorption (Equilibrium, 23°C, 50% RH)	0.060	%	ISO 62
Post Shrinkage	-0.020	%	ISO 2577

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	18000	MPa	ISO 527-2
Tensile Stress	115	MPa	ISO 527-2
Tensile Strain (Break)	0.80	%	ISO 527-2
Flexural Modulus	16000	MPa	ISO 178
Flexural Stress	215	MPa	ISO 178
Compressive Stress	248	MPa	ISO 604

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	51	kJ/m ²	ISO 179

Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	150	°C	TMA
Linear thermal expansion coefficient			TMA
Flow	1.0E-5	cm/cm/°C	TMA
Lateral	5.3E-5	cm/cm/°C	TMA

Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	30	kV/mm	IEC 60243-1
Comparative Tracking Index	600	V	IEC 60112

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

