

DAI-EL™ G-7201

Fluoroelastomer
DAIKIN AMERICA, INC.

Message:
DAI-EL G-7201 is a cure-incorporated copolymer designed for injection transfer and compression molding applications. G-7201 offers low Mooney viscosity with good compression set resistance.

General Information			
Features	Low compressive deformability		
	Low viscosity		
	Copolymer		
Uses	Seals		
Appearance	White		
	Pink		
Forms	Particle		
Processing Method	Compression molding		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.81	g/cm ³	ASTM D792
Mooney Viscosity (ML 1+10, 121°C)	19	MU	ASTM D1646
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	74		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	4.20	MPa	ASTM D412
Tensile Strength (Yield)	13.5	MPa	ASTM D412
Tensile Elongation (Break)	240	%	ASTM D412
Tear Strength (25°C)	23.8	kN/m	ASTM D624
Compression Set			ASTM D395
25°C, 70 hr	11	%	ASTM D395
100°C, 70 hr	9.0	%	ASTM D395
175°C, 70 hr	10	%	ASTM D395
200°C, 70 hr	13	%	ASTM D395
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (230°C, 70 hr)	0.0	%	ASTM D573
Change in Ultimate Elongation in Air (230°C, 70 hr)	8.0	%	ASTM D573

Change in Durometer Hardness in Air (Shore A, 230°C, 70 hr)	2.0		ASTM D573
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-17.0	°C	ASTM D746
Additional Information			


All tests performed were performed under DAIKIN test methodsFluorine Content: 66%Curing characteristic, Measuring Temperature: 170°C Curing characteristic, Curelastomer: 4.6 minGehman torsion test, T2: -5.0°C Gehman torsion test, T10: -14.5°C TR test, TR10: -18°C TR test, TR70: -6°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT