

POLYAXIS® LP 701

High Density Polyethylene

A. Schulman Inc.

Message:

Long term UV8 stabilization

General Information			
Additive	Long Term UV-8 Stabilizer		
Appearance	Black		
	Colors Available		
Forms	Pellets		
	Powder		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	0.945	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield, Rotational Molded)	21.4	MPa	ASTM D638
Tensile Elongation ³ (Break, Rotational Molded)	400	%	ASTM D638
Flexural Modulus - 1% Secant (Rotational Molded)	793	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Impact Strength (-40°C, 3.18 mm, Rotational Molded)	81	J	ARM
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, Rotational Molded)	55.0	°C	ASTM D648
NOTE			
1.	Compression Molded		
2.	51 mm/min		
3.	51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

