

# Jampilen RP1903

Polypropylene Random Copolymer

Jam Polypropylene Company

Message:

Jampilen RP1903 is a random copolymer, suitable for injection stretch blow molding (ISBM) applications. The product features very good transparency and gloss. Jampilen RP1903 is commonly used in packaging of detergents, cosmetics and others where ISBM bottles are used as the packaging.

General Information			
Additive	Nucleating Agent		
Features	Detergent Resistant		
	Good Chemical Resistance		
	Good Impact Resistance		
	High Clarity		
	Nucleated		
	Random Copolymer		
Uses	Bottles		
	Containers		
	Cosmetic Packaging		
	Household Goods		
Processing Method	Injection Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	58.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1100	MPa	ISO 527-2
Tensile Stress (Yield)	30.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	14	%	
Break	> 50	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/A
0°C	2.0	kJ/m <sup>2</sup>	
23°C	6.0	kJ/m <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	72.0	°C	ISO 75-2/B

Optical	Nominal Value	Unit	Test Method
Haze			ASTM D1003
400 μm, Blow Molded	< 3.0	%	
1000 μm, Injection Molded	9.0	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

