

# Manner Flexible PVC C8090 UVAF CL

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

Message:

80°C Clear General Purpose Injection Molding or Clear Tubing. This compound contains an antifungal additive and a UV stabilizer. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General Information			
Additive	Antimicrobial (Fungicide)		
	UV Stabilizer		
Features	Fungus Resistant		
	General Purpose		
Uses	Tubing		
RoHS Compliance	RoHS Compliant		
Appearance	Clear/Transparent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22 to 1.26	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	84 to 90		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	20.0	MPa	ASTM D638
Tensile Elongation (Break)	370	%	ASTM D638
Additional Information	Nominal Value	Unit	
Stock Temperature - Recommended Molding	177	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT