

# Dow ENDURANCE™ HFDA-0587 BK

Crosslinkable Semiconductive Shielding Compound

The Dow Chemical Company

Message:

DOW ENDURANCE™ HFDA-0587 BK is a specially formulated semiconductive, vulcanizable compound designed for use as an extruded strand conductor shield and bonded insulation shield applications in medium voltage crosslinked polyethylene insulated cables.(1) DOW ENDURANCE™ HFDA-0587 BK has stable volume resistivity characteristics at elevated temperatures and is formulated with a polymer system that has demonstrated compatibility with copper and aluminum conductors.

Specifications

DOW ENDURANCE™ HFDA-0587 BK is designed for use in power distribution cables. Cables with conductor and insulation shielding of DOW ENDURANCE™ HFDA-0587 BK, prepared using sound commercial fabrication practice, would be expected to meet the following specifications:

- AEIC: CS8, CS9
- BS: 6622
- CEA: WCWG-01, WCWG-02
- ICEA: S-94-649, S-97-682, S-66-524 (NEMA WC7)
- IEC: 60502, 60840
- DIN: VDE 0273, 0263
- Edf: HN-33-S-23, HN-33-S-52
- ESI: 09-14
- HD: 620 S1
- UL: 1072

(1) DOW ENDURANCE™ HFDA-0587 BK is recommended for use in conjunction with DOW cross-linked polyethylene and tree-retardant cross-linked polyethylene compounds For other polymer insulations such as EPR and EPDM's the user is cautioned to establish the utility of DOW ENDURANCE™ HFDA-0587 BK with each formulation.

General Information	
Uses	Medium Voltage Semiconductive Shield
	Semiconductive Shield
	Underground cable
	Cable guard
	Wire and cable applications
Agency Ratings	AEIC CS8
	AEIC CS9
	BS 6622
	EDF HN 33-S-23
	EDF HN 33-S-52
	HD 620 S1
	ICEA S-66-524
	ICEA S-94-649
	ICEA S-97-682
	IEC 60502
	IEC 60840
	NEMA WC-7
	UL 1072
	VDE 0263

Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm <sup>3</sup>	ASTM D792
Environmental Stress-Cracking Resistance (100% Igepal, F0)	> 504	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	16.9	MPa	ASTM D638
Tensile Elongation (Break)	320	%	ASTM D638
Aging	Nominal Value	Unit	Test Method
Tensile strength retention-1 week (150°C)	95	%	ASTM D638
Elongation retention rate-1 week (150°C)	95	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ASTM D991
23°C	15	ohms · cm	ASTM D991
90°C	40	ohms · cm	ASTM D991
130°C	40	ohms · cm	ASTM D991

#### Additional Information

Nominal property values above represent tests on molded, stress-relieved slabs. Cure times were 15 minutes at 175°C. Storage The environment or conditions of storage greatly influences the recommended storage time. Storage should be in accordance with good manufacturing practices. If proper warehousing and storage temperatures [dry conditions, between 50°F and 86°F (10°C and 30°C) in temperature] are utilized, this product may be stored by the customer for up to one year. It is recommended that the practice of using the product on a first-in / first-out basis be established. Storage under extreme conditions may affect the quality, processing, or performance of the product.

Extrusion	Nominal Value	Unit
Drying Temperature	60.0	°C
Drying Time	< 6.0	hr
Melt Temperature	115 - 140	°C

#### Extrusion instructions

DOW ENDURANCE™ HFDA-0587 BK provides excellent surface finish and outstanding output rates over a broad range of conditions. For optimum results, melt extrusion temperatures in the suggested range of 240 to 285°F (115 to 140°C) to avoid pre-cure or scorch. Extruder barrel settings of 110°C (230°F) are suggested as a starting point while learning to process DOW ENDURANCE™ HFDA-0587 BK. Specific machine settings will depend on the extruder design and must be established through conventional practices. Dehumidified hopper drying at 140°F (60°C) for up to 6 hours may be employed to remove moisture prior to extrusion.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

