

AKROMID® A3 1 natural (2416)

Polyamide 66
AKRO-PLASTIC GmbH

Message:

AKROMID® A3 1 natural (2416) is a heat stabilised, unreinforced polyamide 6.6 with light inherent color
Applications are housings and fixtures in automotive and electric industry

General Information				
UL YellowCard		E148915-101092093		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
Uses		Automotive Applications		
		Electrical/Electronic Applications		
		Housings		
Appearance		Natural Color		
Resin ID (ISO 1043)		PA66		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.14	--	g/cm ³	ISO 1183
Spiral Flow	104	--	cm	Internal Method
Molding Shrinkage				ISO 294-4
Across Flow	2.3	--	%	
Flow	1.9	--	%	
Water Absorption (Saturation, 23°C)	8.0 to 9.0	--	%	ISO 62
Humidity Absorption - 62% RH (70°C)	2.9 to 3.1	--	%	ISO 1110
Temperature Index				IEC 216
50% Loss of Tensile Strength, 20000 hr	100 to 120	--	°C	
50% Loss of Tensile Strength, 5000 hr	115 to 145	--	°C	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3200	1100	MPa	ISO 527-2/1
Tensile Stress (Yield)	85.0	50.0	MPa	ISO 527-2/50
Tensile Strain (Break)	> 20	> 50	%	ISO 527-2/50
Flexural Modulus ¹	2800	--	MPa	ISO 178
Flexural Stress ²	110	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	2.0	3.0	kJ/m ²	

23°C	5.0	13	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	215	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	75.0	--	°C	ISO 75-2/A
Melting Temperature ³	262	--	°C	DIN EN 11357-1
CLTE				ISO 11359-2
Flow : 23 to 80°C	7.1E-5	--	cm/cm/°C	
Transverse : 23 to 80°C	1.1E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+13	1.0E+10	ohms·cm	IEC 60093
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate ⁴ (1.00 mm)	< 100	--	mm/min	FMVSS 302
Flame Rating (0.800 mm)	V-2	--		UL 94
Glow Wire Flammability Index (1.60 mm)	750	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.60 mm)	675	--	°C	IEC 60695-2-13
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			
3.	10 K/min, DSC			
4.	>1 mm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT