

Sindustris PC SC1005AU

Polycarbonate
Sincerity Australia Pty Ltd.

Message:

Sindustris PC SC1005AU is a Polycarbonate (PC) material. It is available in Asia Pacific for injection molding.
Important attributes of Sindustris PC SC1005AU are:
Flame Rated
Good Weather Resistance
High Flow
Impact Resistant
Typical applications include:
Electrical/Electronic Applications
Housings

General Information			
Features	Good Weather Resistance		
	High Flow		
	High Impact Resistance		
Uses	Electrical/Electronic Applications		
	Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	22	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	54.9	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	130	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2110	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	89.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	290	J/m	
23°C, 3.20 mm	590	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	125	°C	ASTM D648
RTI Elec	80.0	°C	UL 746

RTI Imp	80.0	°C	UL 746
RTI Str	80.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating (0.700 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100 to 110	°C	
Drying Time	3.0 to 5.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	275 to 290	°C	
Middle Temperature	280 to 295	°C	
Front Temperature	290 to 300	°C	
Nozzle Temperature	285 to 300	°C	
Processing (Melt) Temp	285 to 300	°C	
Mold Temperature	80.0 to 110	°C	
Back Pressure	0.981 to 3.92	MPa	
Screw Speed	40 to 70	rpm	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	10 mm/min		
4.	10 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT