

Epoxies, Ect. 20-3035 (Cat.30)

Epoxies; Epoxide

Epoxies, Etc.

Message:

20-3035 is a low density, two component epoxy potting and encapsulating system. The 20-3035 is less than half the weight of most commercially available potting compounds.

20-3035 exhibits very low shrinkage during the cure cycle and also has a low coefficient of thermal expansion. This unique epoxy system is an ideal material for the potting of electronic assemblies where a low dielectric constant and low weight are required.

This epoxy syntactic foam system utilizes an advanced micro balloon technology filler. The 20-3035 provides high strength and stiffness, thermal and environmental stability, creep resistance, and water resistance.

Features:

- Low Dielectric Constant
- Low Coefficient of Thermal Expansion
- Low Shrinkage
- Low Density
- Excellent Moisture Resistance

General Information		
Features	Good Creep Resistance	
	Good Thermal Stability	
	High Stiffness	
	High Strength	
	Low Density	
	Low Shrinkage	
	Low to No Water Absorption	
Uses	Electrical/Electronic Applications	
Processing Method	Encapsulating	
	Potting	
Physical	Nominal Value	Unit
Molding Shrinkage - Flow	0.20	%
Mechanical	Nominal Value	Unit
Flexural Strength	46.9	MPa
Thermal	Nominal Value	Unit
CLTE - Flow	4.0E-5	cm/cm/°C
Thermal Conductivity	0.19	W/m/K
Thermoset	Nominal Value	Unit
Thermoset Mix Viscosity (25°C)	15000	cP
Additional Information	Nominal Value	Unit
Operating Temperature	-55.0 to 155	°C
Outgassing		
% CVC	0.0600	
% TMLV	0.490	

Uncured Properties	Nominal Value	Unit
Mix Ratio by Weight (PBW)		
Part A	100	
Part B	21	
Density (25°C)	0.828	g/cm ³
Viscosity ¹ (25°C)	45	Pa·s
Curing Time		
100°C	2.0 to 3.0	hr
85°C	3.0 to 4.0	hr
Pot Life ² (25°C)	240	min
Cured Properties	Nominal Value	Unit
Water Absorption ³	0.050	%
Shore Hardness (Shore D)	82	
Tensile Strength	33.1	MPa
Compression Strength	82.7	MPa
Electric Strength	15	kV/mm
Relative Permittivity (1 MHz)	2.73	
Volume Resistivity (25°C)	> 1.0E+13	ohms·cm
Dissipation Factor (1 MHz)	0.050	
NOTE		
1.	Part A	
2.	100 grams	
3.	After 24 hours	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT