

Hostalen GD 9550 F

High Density Polyethylene
LyondellBasell Industries

Message:

Hostalen GD 9550F is a high density polyethylene. Films made of Hostalen GD 9550F provide a good barrier against water vapour. It contains antioxidants and is delivered in pellet form.
Foodlaw compliance information about this product can be found in separate product documentation.
This product is not intended for use in medical and pharmaceutical applications.

General Information			
Additive	Antioxidation		
Features	Low speed solidification crystal point		
	Moisture proof		
	Antioxidation		
	Good liquidity		
Uses	Packaging		
	Films		
	Food packaging		
	Plastic modification		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.950	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/21.6 kg	34	g/10 min	ISO 1133
190°C/5.0 kg	3.1	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	950	MPa	ISO 527-2
Tensile Stress (Yield)	23.0	MPa	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	30	µm	
Film Thickness - Recommended / Available	0.8-3.1 mil (20-80 µ)		
Tensile Strength			ISO 527-3
MD: 30 µm, blown film	55.0	MPa	ISO 527-3
TD: 30 µm, blown film	50.0	MPa	ISO 527-3
Tensile Elongation - MD (Broken, 30 µm, blown film)	600	%	ISO 527-3
Dart Drop Impact (30 µm, Blown Film)	50	g	ASTM D1709

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	72.0	°C	ISO 306/B50
Additional Information	Nominal Value	Unit	Test Method
Staudinger Index	230	cm ³ /g	ISO 1628
Film properties tested using 30 µm thickness blown film extruded at a melt temperature of 190°C and a blow-up ratio of 2.65:1.			
Extrusion	Nominal Value	Unit	
Melt Temperature	180 - 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

