InnoPlus HD1100J

High Density Polyethylene

PTT Global Chemical Public Company Limited

Message:

InnoPlus HD1100J and HD1600J are high density polyethylene injection molding grade. They are tailored with narrow molecular weight distribution (MWD) and high flow ability. They have optimum strength property which used for general part, auto part, toy and house ware. Typical Application: Toys, Auto parts, Household products

General Information					
Features	Food Contact Acceptable				
	Good Strength				
	High Flow				
	Narrow Molecular Weight Distribution				
Uses	Automotive Applications				
	General Purpose				
	Household Goods				
	Toys				
Agency Ratings	FDA 21 CFR 177.1520				
RoHS Compliance	RoHS Compliant				
Forms	Pellets				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	0.958	g/cm³	ASTM D1505		
Melt Mass-Flow Rate (MFR) (190°C/2.16					
kg)	18	g/10 min	ASTM D1238		
ESCR - condition B, 25% Igepal, F50	Initial Break		ASTM D1693		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D)	64		ASTM D2240		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength			ASTM D638		
Yield	29.4	MPa			
Break	22.6	MPa			
Tensile Elongation (Break)	60	%	ASTM D638		
Apparent Bending Modulus	981	MPa	ASTM D747		
Flexural Modulus	1230	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact ¹	39	J/m	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		
Vicat Softening Temperature	116	°C	ASTM D1525 ²		

Peak Melting Temperature	128	°C	ASTM D3418
Injection	Nominal Value	Unit	
Rear Temperature	165 to 190	°C	
Middle Temperature	165 to 190	°C	
Front Temperature	165 to 190	°C	
Nozzle Temperature	180 to 195	°C	
NOTE			
1.	Complete break		
2.	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

