# WPP TPO TPO-2563 P Black

### Compounded Polypropylene

Washington Penn Plastic Co. Inc.

#### Message:

WPP TPO TPO-2563 P Black is a composite polypropylene product containing 26% mineral fillers. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: automotive industry.

Features include:

Hard

Good toughness

Impact resistance

soft

UV stability

General Information					
Filler / Reinforcement	Mineral filler, 26% filler by weight				
Additive	UV stabilizer				
Features	Impact resistance, good				
	Medium liquidity				
	Good toughness				
	ductility				
	Medium hardness				
Uses	Application in Automobile Field				
	Automotive exterior parts				
Appearance	Black				
	Available colors				
Forms	Particle				
Physical	Nominal Value	Unit	Test Method		
Density	1.10	g/cm³	ISO 1183		
Melt Mass-Flow Rate (MFR) (230°C/2.16					
kg)	12	g/10 min	ISO 1133		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D, 15 sec)	60		ISO 868		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Stress (Break)	14.0	МРа	ISO 527-2/50		
Tensile Strain (Break)	200	%	ISO 527-2/50		
Flexural Modulus <sup>1</sup>	1200	MPa	ISO 178		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact			ISO 180		
-40°C	3.5	kJ/m²	ISO 180		
23°C	38	kJ/m²	ISO 180		

Instrumented Dart Impact <sup>2</sup>			ASTM D3763	
-30°C	22.0	J	ASTM D3763	
23°C	18.0	J	ASTM D3763	
Thermal	Nominal Value	Unit	Test Method	
Heat Deflection Temperature				
0.45 MPa, not annealed	90.0	°C	ISO 75-2/B	
1.8 MPa, not annealed	68.0	°C	ISO 75-2/A	
Linear thermal expansion coefficient			ASTM E831	
Flow	4.0E-5	cm/cm/°C	ASTM E831	
Lateral	1.5E-4	cm/cm/°C	ASTM E831	
Additional Information				
Tensile Strain at Break, ISO 527, 50mm/min: >200%				
NOTE				
1.	2.0 mm/min			
2.	2.20 m/sec			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

