

KetaSpire® KT-880SFP

Polyetheretherketone

Solvay Specialty Polymers

Message:

KetaSpire® KT-880SFP is the high flow grade of unreinforced polyetheretherketone (PEEK) supplied in a natural-color super-fine powder form. This super-fine PEEK powder is suitable for water borne coatings, electrostatically driven powder coatings, and resin pre-impregnation of continuous fiber composites. This super-fine powder is produced to a median particle size D50 of about 30 micrometers.

KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent chemical resistance to acids, bases and a broad range of aggressive organic chemicals, best in class fatigue resistance, high thermal resistance, high purity and ease of melt processing.

These properties make KT-880SFP well-suited for applications in health care, transportation, electronics, chemical processing and other industrial uses. The resin is also available in a natural-colored pellet form under the grade name KT-880 NT for injection molding applications.

General Information	
Features	Good dimensional stability
	Impact resistance, good
	Good chemical resistance
	Fatigue resistance
	Heat resistance, high
	ductility
	Flame retardancy
Uses	Electrical/Electronic Applications
	Industrial application
	Aerospace applications
	Application in Automobile Field
	Oil/Gas Supplies
RoHS Compliance	Contact manufacturer
Appearance	Natural color
Forms	Powder
Processing Method	Water-borne Coating
	Electrostatic jet coating

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Water Absorption (24 hr)	0.10	%	ASTM D570
Particle Size			
D50	30.0	µm	
D90	55.0	µm	
D99	120	µm	
Mechanical	Nominal Value	Unit	Test Method

Tensile Modulus	3650	MPa	ASTM D638
Tensile Strength	100	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	5.2	%	ASTM D638
Fracture ¹	10 - 20	%	ASTM D638
Flexural Modulus	3790	MPa	ASTM D790
Flexural Strength	153	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Unnotched Izod Impact	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	160	°C	ASTM D648
Glass Transition Temperature	147	°C	ASTM D3417
Melting Temperature	343	°C	ASTM D3417
CLTE - Flow (-50 to 50°C)	5.0E-5	cm/cm/°C	ASTM E831
Injection instructions			
Back Pressure: minimum			
NOTE			

1. Tensile test speed = 2 in/min (50 mm/min)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT